

# Activated Alumina JZ-K2

## Description:

JZ-K2 activated alumina is specially designed. Compared with JZ-K1, with 20% increase of water adsorption and surface area.

## Applications:

Air dryer/ Air separation systems

## Specification:

Properties	Unit	JZ-K2	
Diameter	mm	3-5	4-6
Bulk Density	≥g/ml	0.68	0.67
Surface Area	≥m <sup>2</sup> /g	360	360
Pore Volume	≥ml/g	0.38	0.36
Crush Strength	≥N/Pc	110	150
L.O.I.	≤%	8	8
Attrition Rate	≤%	0.3	0.3

## Standard Package:

25 kg/woven bag

150 kg/steel drum

## Attention:

The product as desiccant cannot be exposed in the open air and should be stored in dry condition with air-proof package.

