

Activated Alumina JZ-K3

Description:

JZ-K3 activated alumina has a dynamic adsorption capacity 1/3 higher than normal activated alumina under the same test conditions, and is especially suitable for heatless air dryer. due to its easy desorption and regeneration.

Applications:

Air dryer/ Air separation systems

Specification:

Properties	Unit	JZ-K3
Diameter	mm	3-5
Bulk Density	≥g/ml	0.75
Crush Strength	≥N/Pc	150
L.O.I.	≤%	8
Attrition Rate	≤%	0.3

Standard Package:

25 kg/woven bag
150 kg/steel drum

Attention:

The product as desiccant cannot be exposed in the open air and should be stored in dry condition with air-proof package.

